

Svařovací tabulka pro ST 160 pro dimenzi 40 - 160 mm pro PVDF

Dim (mm)	Síla stěny (mm)	Tlaková řada (PN)	SDR	Orovn. síla (kg)	Natav. síla (kg)	Výška nákrůžku (mm)	Doba nahřívání (s)	Doba přestavení max. (s)	Náběh tlaku max. (s)	Svařovací síla (kg)	Doba chladnutí (min)
40	2,4		16,7	4,0	1,0	0,5	64	4	4	4,0	6
50	3,0		16,7	6,0	1,0	0,5	70	4	4	6,0	6
63	2,0	10	31,5	4,0	1,0	0,5	60	4	4	4,0	6
63	3,0	16	21	6,0	1,0	0,5	70	4	4	6,0	6
75	2,3	10	32,6	6,0	1,0	0,5	64	4	4	6,0	6
75	2,5	10	30	6,0	1,0	0,5	66	4	4	6,0	6
75	3,6	16	20,8	10,0	1,0	0,5	76	4	5	10,0	7
75	4,3		17,4	10,0	1,0	0,5	84	4	5	10,0	8
90	2,8	10	32,1	8,0	1,0	0,5	68	4	4	8,0	6
90	4,3	16	20,9	12,0	2,0	0,5	84	4	5	12,0	8
90	5,1		17,6	14,0	2,0	0,5	92	4	5	14,0	8
110	3,0	10	36,7	12,0	2,0	0,5	70	4	4	12,0	6
110	3,5	10	31,4	12,0	2,0	0,5	76	4	4	12,0	6
110	5,3	16	20,8	18,0	2,0	0,5	94	4	5	18,0	9
110	6,3		17,5	22,0	3,0	0,6	104	4	6	22,0	10
125	3,0		41,7	12,0	2,0	0,5	70	4	4	12,0	6
125	3,9	10	32,1	16,0	2,0	0,5	80	4	5	16,0	7
125	6,0	16	20,8	24,0	3,0	0,6	100	4	6	24,0	10
140	3,0		46,7	14,0	2,0	0,5	70	4	4	14,0	6
140	4,4	10	31,8	20,0	2,0	0,5	84	4	5	20,0	8
140	6,8	16	20,6	30,0	3,0	0,6	108	4	6	30,0	11
160	3,0		53,3	16,0	2,0	0,5	70	4	4	16,0	6
160	5,0	10	32	26,0	3,0	0,5	90	4	5	26,0	8
160	7,7	16	20,8	38,0	4,0	0,7	118	4	6	38,0	12