

Svařovací tabulka pro STH 630 pro dimenzi 315 - 630 mm pro PVDF

Dim (mm)	Síla stěny (mm)	Tlaková řada (PN)	SDR	Orovn. tlak (bar)	Natav. tlak (bar)	Výška nákrůžku (mm)	Doba nahřívání (s)	Doba přestavení max. (s)	Náběh tlaku (s)	Svařovací přítlak (bar)	Doba chlazení (min)
315	7,7	10	41	4,0	1,0	0,7	118	4	6	4,0	12
315	9,8		33	4,0	1,0	1	138	4	7	4,0	14
315	12,2		26	6,0	1,0	1,1	162	4	8	6,0	17
315	17,9		17,6	8,0	1,0	1,5	220	6	11	8,0	23
315	28,7		11	10,0	1,0	2,2	328	6	15	10,0	38
355	8,7	10	41	4,0	1,0	0,9	128	4	7	4,0	13
355	11,1		33	6,0	1,0	1,1	152	4	8	6,0	16
355	13,7		26	6,0	1,0	1,2	178	4	9	6,0	18
355	20,1		17,6	8,0	1,0	1,7	242	6	12	8,0	26
355	32,3		11	14,0	2,0	2,4	364	6	16	14,0	43
400	9,8	10	41	6,0	1,0	1	138	4	7	6,0	14
400	12,4		33	6,0	1,0	1,1	164	4	8	6,0	17
400	15,4		26	8,0	1,0	1,3	194	6	10	8,0	20
400	22,7		17,6	10,0	1,0	1,9	268	6	13	10,0	29
400	36,4		11	16,0	2,0	2,7	404	6	18	16,0	48